

DCMT 11T304 NN

Machining Conditions

Material Group	Group No.	Material Examples*	Brinell hardness HB	d.o.c [mm]		feed [mm/rev]		A max [mm ²]	V _c [m/min]		Optimal cutting conditions		
				min	max	min	max		min	max	d.o.c	feed	
Low Carbon Steel	1	Ck15 9SMnPb28	150	0.20	3.00	0.11	0.23	0.60	180	400	0.5 to 2	0.18	
			180		2.50		0.20	0.60		350			
			210		2.50		0.18	0.48		200			
Alloy Steel	2	42 CrMo 4 100 Cr 6 32 NiCrMo 14.5	180	0.20	2.50	0.11	0.20	0.48	120	300	0.5 to 1.5	0.15	
			230		2.50		0.20	0.40		250			
			280		2.00	0.09	0.18	0.40		210			
			320		2.00		0.16	0.32		180			
High Alloy Steel	3	X38 CrMoV 5 X210 CrW 12 X90 CrMoV 8	220	0.20	2.50	0.09	0.18	0.40	70	190	0.5 to 1.5	0.12	
			280		2.50		0.16	0.40		150			
			320		2.00		0.14	0.28		130			
			350		2.00		0.14	0.24		100			
Austenitic Stainless Steel	4	303 / 304 304 L	210 to 250	0.20	2.50	0.10	0.18	0.32	170	270	0.5 to 2	0.15	
			230 to 270		2.00		0.09	0.16		0.24			210
			316 Ti 630 (F16PH)		2.00		0.09	0.14		0.20			80
Ferritic Stainless Steel	7	430 / 439 / 444	Annealed	0.20	2.00	0.11	0.18	0.28	170	250	0.5 to 1.5	0.15	
Martensitic Stainless Steel	8	410 / 420	Annealed Treated	0.20	2.00	0.11	0.18	0.28	170 120	250 210	0.5 to 1.5	0.15	
Grey Cast Iron	9	EN - GJL 200 EN - GJL 250 EN - GJL 300	140 to 230	0.20	3.00	0.08	0.20	0.64	170	280	0.5 to 2	0.18	
			0.60					250					
			0.60					230					
Nodular Cast Iron	10	EN - GJS 400 EN - GJS 600 EN - GJS 800	210	0.20	2.50	0.08	0.18	0.48	120	230	0.5 to 1.5	0.15	
			260					0.40		190			
			310					0.40		150			
Nickel Based Alloys	11	Inconel 625 Inconel 718 Hastelloy C	-----	0.25	2.00	0.1	0.16	0.24	25	35	0.5 to 1.5	0.12	
			-----					0.24		40			
			-----					0.28		65			
Titanium Based Alloys	12	TiAl 6 V4 T40	-----	0.25	2.00	0.09	0.16	35	60	0.5 to 1.5	0.14		
			-----				0.14		0.24			28	40

*For all material types and standards, see pages 155 to 158.

Insert designation **Super Finishing** **Finishing** **Semi Finishing** **Roughing** **Interrupted Cut**

DCMT 11T304 NN



Lamina Technologies