

SNMG 120408 NN

Machining Conditions

Material Group	Group No.	Material Examples*	Brinell hardness HB	d.o.c [mm]		feed [mm/rev]		A max [mm ²]	V _c [m/min]		Optimal cutting conditions	
				min	max	min	max		min	max	d.o.c	feed
Low Carbon Steel	1	Ck 15 9SMnPb28	150	0.50	5.00	0.21	0.54	1.80	180	400	1.5 to 3	0.35
			180		5.00		0.54	1.80		350		
			210		4.00		0.48	1.50		200		
Alloy Steel	2	42 CrMo 4 100 Cr 6 32 NiCrMo 14.5	180	0.50	5.00	0.21	0.48	1.50	120	300	1.5 to 3	0.30
			230		4.00		0.48	1.20		250		
			280		4.00		0.42	1.20		210		
			320		3.50		0.42	1.00		180		
High Alloy Steel	3	X38 CrMoV 5 X210 CrW 12 X90 CrMoV 8	220	0.50	4.00	0.18	0.48	1.20	70	190	1.5 to 3	0.28
			280		4.00		0.48	1.20		150		
			320		3.00		0.42	0.80		130		
			350		3.00		0.42	0.80		100		
Austenitic Stainless Steel	4	303 / 304 304 L	Annealed	0.50	5.00	0.20	0.40	1.00	170	270	1.5 to 3	0.35
	5	316 / 316 L	Annealed		4.00	0.18	0.35	0.80	170	210	1.5 to 3	0.32
	6	316 Ti 630 (F16PH)	Annealed		4.00	0.18	0.35	0.60	80	130	1.5 to 3	0.28
Ferritic Stainless Steel	7	430 / 439 / 444	Annealed	0.50	4.00	0.22	0.35	0.90	170	250	1.5 to 3	0.32
Martensitic Stainless Steel	8	410 / 420	Annealed Treated	0.50	4.00	0.22	0.35	0.90	170 120	250 210	1.5 to 3	0.32
Grey Cast Iron	9	EN - GJL 200	140 to 230	0.50	5.00	0.15	0.72	2.00	170	280	1.5 to 3	0.35
		EN - GJL 250						1.80		250		
		EN - GJL 300						1.80		230		
Nodular Cast Iron	10	EN - GJS 400	210	0.50	5.00	0.15	0.60	1.50	120	230	1.5 to 3	0.30
		EN - GJS 600						1.30		190		
		EN - GJS 800						1.20		150		
Nickel Based Alloys	11	Inconel 625	-----	0.50	3.00	0.20	0.42	0.70	25	35	1.5 to 3	0.28
		Inconel 718						0.70		40		
		Hastelloy C						0.80		65		
Titanium Based Alloys	12	TiAl 6 V4	-----	0.50	3.00	0.18	0.42	35	60	1.5 to 3	0.30	
		T40					0.36		0.60			28

*For all material types and standards, see pages 155 to 158.



SNMG